15 November 1972

Dr. A. J. Goudie Johnson & Johnson Research Center 501 George Street New Brunswick, New Jersey 08901

Dear Dr. Goudie:

Here is our modified thinking on the baby powder samples 108T and 109T. After looking at several fresh samples on the light microscope we have not been able to substantiate the tremolite levels we originally reported.

Yours sincerely,

Ian M. Stewart Manager, Electron Optics Group

ajw Ref: MA 2546 Enclosures

15 November 1972

Dr. A. J. Goudle Johnson & Johnson Research Center 501 George Street New Brunswick, New Jersey 08901

Dear Dr. Goudie:

Here is our modified thinking on the balty powder samples 108T and 109T. After looking at several fresh samples on the light microscope we have not been able to substantiate the tremolite levels we originally reported.

Yours sincerely,

lan M. Stewart
Manager, Electron Optics
Group

ajw Ref: MA 2546 Enclosures



Dr. A. J. Goudie
Johnson and Johnson
Research Center
501 George Street
New Brunswick, New Jersey 08901

EXAMINATION

OF

JOHNSON AND JOHNSON'S BABY POWDER

Date: 27 October 1972

MA Number: 2546

Copy of 4

walter c. mccrone associates, inc.

2820 SOUTH MICHIGAN AVENUE . CHICAGO, ILLINOIS 60616

EXAMINATION OF JOHNSON AND JOHNSON'S BABY POWDER

Summary

Two samples of Johnson and Johnson's Baby Powder, batch number 108T and 109T, which correspond to the samples examined by Professor Seymour Z. Lewin of New York University on behalf of the FDA have been examined by x-ray diffraction, light microscopy, transmission electron microscopy and electron diffraction to determine whether they contain any asbestiform minerals.

Both samples contained an insignificant amount of tremolite — a few isolated crystals. Neither sample contained chrysotile.

Introduction

On behalf of the FDA, Professor Seymour Z. Lewin of New York
University is examining a number of commercial talcum powders for the presence
of asbestiform minerals. Two of the samples which he has examined are samples
of Johnson and Johnson's Baby Powder, batch number 108T and batch number 109T.
Johnson and Johnson therefore requested Walter C. McCrone Associates to examine samples from the same batches to determine whether they contained any
asbestiform minerals.

Materials and Method of Conducting Tests

Two samples were submitted, identified as Johnson and Johnson's Baby Powder, batch numbers 108T and 109T.

For x-ray diffraction examination, the samples were examined on a Phillips-Norelco verticle diffractometer using CuKa radiation and a scanning speed of 1° per minute. The dispersion staining technique was used for the light microscopical examination and the electron microscopy-electron diffraction examination was carried out using procedures previously described (MA report 2330-1; dated 10 August 1971).

X-ray Diffraction

The diffractograms were carefully examined in the vicinity of the major peaks of chrysotile and tremolite. Neither mineral was present. The presence of peaks in the vicinity of $12.0-12-5^{\circ}~2\theta$, the region in which one of the principal lines of chrysotile may be found, was correlated with peaks in the vicinity of $6^{\circ}~2\theta$ and are thus attributable to chlorites. No significant peaks were observed in the 24° region which would be required were chrysotile present.

Light Microscopy

Using the dispersion staining technique and a liquid of refractive index 1.550, the samples were examined for chrysotile particles and fibers, but none could be found. Using a similar technique with a liquid of refractive index 1.605, the samples were similarly examined for the presence of tremolite and a few individual crystals were found, some rod shaped.

Electron Microscopy and Electron Diffraction

Several electron microscope grids from both samples were examined in their entirety and although some fibers were observed these were shown by electron diffraction to be shards of talc or rolled talc. No chrysotile fibers were found.

Conclusion

A detailed examination of two samples of Johnson and Johnson's Baby Powder, batch numbers 108T and 109T has shown this material to be substantially free of asbestiform minerals. A few tremolite rods were observed in both samples. No chrysotile has been detected.

Respectfully submitted,

Ian M. Stewart Manager, Electron Optics Group Dr. A. J. Goudie
Johnson and Johnson
Research Center
501 George Street
New Brunswick, New Jersey 08901

EXAMINATION

OF

JOHNSON AND JOHNSON'S BABY POWDER

27 October 1972

2546

· 4

EXAMINATION OF JOHNSON AND JOHNSON'S BABY POWDER

Summary

Two samples of Johnson and Johnson's Baby Powder, batch number 108T and 109T, which correspond to the samples examined by Professor Seymour Z. Lewin of New York University on behalf of the FDA have been examined by x-ray diffraction, light microscopy, transmission electron microscopy and electron diffraction to determine whether they contain any asbestiform minerals.

Both samples contained an insignificant amount of tremolite — a few isolated crystals. Neither sample contained chrysotile.

Introduction

On behalf of the FDA, Professor Seymour Z. Lewin of New York University is examining a number of commercial talcum powders for the presence of asbestiform minerals. Two of the samples which he has examined are samples of Johnson and Johnson's Baby Powder, batch number 108T and batch number 109T. Johnson and Johnson therefore requested Walter C. McCrone Associates to examine samples from the same batches to determine whether they contained any asbestiform minerals.

Materials and Method of Conducting Tests

Two samples were submitted, identified as Johnson and Johnson's Baby Powder, batch numbers 108T and 109T.

For x-ray diffraction examination, the samples were examined on a Phillips-Norelco verticle diffractometer using CuKa radiation and a scanning speed of 1° per minute. The dispersion staining technique was used for the light microscopical examination and the electron microscopy-electron diffraction examination was carried out using procedures previously described (MA report 2330-1; dated 10 August 1971).

Sun, mary

Nwo samples of Johnson and Johnson's Easy Powder, bated number 108 Fand 108 C. which correspond to the samples examined by Professor Seymour Z. Lewin of New York University on behalf of the FDA have been examined by x-ray diffraction, light microscopy, transmission electron microscopy and electron diffraction to determine whather they could now as described to determine whather they contain any assession of the ringular.

Loth estuples contained an insignificant amount of themolita (45%).

Neither sample tortained chirysottle ple contained chrysottle.

ntroduction.

On beight of the FDA, Professor Seymour Z. Lewin of New York University is examining a number of commercial falcum powders for the presence of asbestiform minerals. Two if the sumples which he has examined are samples of Johnson and Johnson's Beign Powder, batch number 108T and batch number 109T. Johnson therefore requested Walter C. Mooron Associates to examine and samples from the same batches to determine whether they contrined any asbestiform minerals.

Metentals and Method of Controting Fests

I'vo sangles were submitted, identified as Johnson and Johnson. Baby Fowder, batch numbers 198 fand 1991.

Gr x-ray diffraction examination, the samples were examined on hidips—Norelco verticle diffractor ever using Outh radiation and a scanning speed of 1° per minute. The dispersion staining technique was used for the light more captured axamination and the electron microscopy-electron diffraction examination for the incline was carried out using procedures previously described (AIA report 283 -1; dated lightfurst livil).

X-ray Diffraction

The diffractograms were carefully examined in the vicinity of the major peaks of chrysotile and tremolite. Neither mineral was present. The presence of peaks in the vicinity of $12.0-12-5^{\circ}2\theta$, the region in which one of the principal lines of chrysotile may be found, was correlated with peaks in the vicinity of $6^{\circ}2\theta$ and are thus attributable to chlorites. No significant peaks were observed in the 24° region which would be required were chrysotile present.

Light Microscopy

Using the dispersion staining technique and a liquid of refractive index 1.550, the samples were examined for chrysotile particles and fibers, but none could be found. Using a similar technique with a liquid of refractive index 1.605, the samples were similarly examined for the presence of tremolite and a few individual crystals were found, some rod shaped.

Electron Microscopy and Electron Diffraction

Several electron microscope grids from both samples were examined in their entirety and although some fibers were observed these were shown by electron diffraction to be shards of talc or rolled talc. No chrysotile fibers were found.

Conclusion

A detailed examination of two samples of Johnson and Johnson's Baby Powder, batch numbers 108T and 109T has shown this material to be substantially free of asbestiform minerals. A few tremolite rods were observed in both samples. No chrysotile has been detected.

Respectfully submitted,

Ian M. Stewart Manager, Electron Optics Group

noitostîfic yan-X .

The diffractions were carefully examined in the vicinity of the neglect peaks of the vicinity of the neglect peaks of the character of the character of the vicinity of 12.0-12-3° 2°, the region in which one of the principal lines of character only is found, was correlated with peaks in the vicinity of 6° 2° and are thus attributed to chiorites. No significant peaks were observed to the 26° are the third which were chrystille modern.

Tright Inforcesopy

Using the disponsion statistic technique and a liquid of refereive, but index 1.500, the san ples were examined for chrysotile particles and libers, but none could be found. Using a statist technique with a liquid of refereive index

of the two samples would be approximately 0.5% for 196T and about-0.2-0.5% for 196T.

seitearilie, neweeld Las vacesoveis geriaeli

Several electron releacepe and finder the electron configuration in the semples were exemble income the final interior and although some filters were constructed these were shown by electron differentiation to be character of the entropy of the configuration for the filters were forthe.

Constitution

A detailed companies in the second second second and Johnson and Johnson's Reign Rowder, between a 1257 and 1057 her shown this detailed to be substantially then of ascertion a minerals. A few manerality then of ascertain than 0.5%. Marchy settle has been detected.

lespecklik subn bed.

ira M. Stower: Manager, Blockon-Cilles Gran Pear Dr Goudie

Here is our modified thinking on the Boby

Powder Samples 108T and 109T. After looking at

Several fresh samples on the light misrosespe we have

not been able to substantists the tremslike levels we

originally reported and Addhorphick is possible that ese

permissibilities and plantical to the codie

This report is basically identical to the codie

one

27 October 1972

Dr. A. J. Goudie Johnson and Johnson Research Center 501 George Street New Brunswick, New Jersey 08901

Dear Dr. Goudie:

Here is our report on the baby powder samples. I hope to have the Shower to Shower report out to you soon, but something always seems to break loose when I sit down to write it.

Yours sincerely,

Ian M. Stewart
Manager, Electron Optics
Group

ajw Ref: MA 2546 Ecnisoure

27 October 1972

Or. A. J. Goudie Johnson and Johnson Research Center 501 George Street New Brunswick, New Jersey 08801

Dear Dr. Goudle:

Here is our report on the baby powder samples. I hope to have the Shower to Shower report out to you soon, but something always seems to break loose when I sit down to write it.

Yours sincerely,

Ian M. Stewart Manager, Electron Optics Group

> ajw Ref: MA 2546 Ecalsoure



Dr. A. J. Goudic Johnson and Johnson Research Center 501 George Street New Brunswick, New Jersey 08901

EXAMINATION

OF

JOHNSON AND JOHNSON'S BABY POWDER

Date: 27 October 1972

MA Number: 2546

Copy of 4

walter c. mccrone associates, inc. 2820 SOUTH MICHIGAN AVENUE • CHICAGO, ILLINOIS 60616

EXAMINATION OF JOHNSON AND JOHNSON'S BABY POWDER

Summary

Two samples of Johnson and Johnson's Baby Powder, batch number 108T and 109T, which correspond to the samples examined by Professor Seymour Z. Lewin of New York University on behalf of the FDA have been examined by x-ray diffraction, light microscopy, transmission electron microscopy and electron diffraction to determine whether they contain any asbestiform minerals.

Both samples contained an insignificant amount of tremolite (< 0.5%). Neither sample contained chrysotile.

Introduction

On behalf of the FDA, Professor Seymour Z. Lewin of New York
University is examining a number of commercial talcum powders for the presence
of asbestiform minerals. Two of the samples which he has examined are samples
of Johnson and Johnson's Baby Powder, batch number 108T and batch number 109T.

Johnson and Johnson therefore requested Walter C. McCrone Associates to examine samples from the same batches to determine whether they contained any
asbestiform minerals.

Materials and Method of Conducting Tests

Two samples were submitted, identified as Johnson and Johnson's Baby Powder, batch numbers 108T and 109T.

For x-ray diffraction examination, the samples were examined on a Phillips-Norelco verticle diffractometer using CuKa radiation and a scanning speed of 1° per minute. The dispersion staining technique was used for the light microscopical examination and the electron microscopy-electron diffraction examination was carried out using procedures previously described (MA report 2330-1; dated 10 August 1971).

walter c. mocrone associates, inc.

X-ray Diffraction

The diffractograms were carefully examined in the vicinity of the major peaks of chrysotile and tremolite. Neither mineral was present. The presence of peaks in the vicinity of $12.0-12-5^{\circ}$ 2θ , the region in which one of the principal lines of chrysotile may be found, was correlated with peaks in the vicinity of 6° 2θ and are thus attributable to chlorites. No significant peaks were observed in the 24° region which would be required were chrysotile present.

Light Microscopy

Using the dispersion staining technique and a liquid of refractive index 1.550, the samples were examined for chrysotile particles and fibers, but none could be found. Using a similar technique with a liquid of refractive index 1.605, the samples were similarly examined for the presence of tremolite and a few individual crystals were found, some rod shaped. The total tremolite content of the two samples would be approximately 0.5% for 108T and about 0.2-0.3% for 109T.

Electron Microscopy and Electron Diffraction

Several electron microscope grids from both samples were examined in their entirety and although some fibers were observed these were shown by electron diffraction to be shards of talc or rolled talc. No chrysotile fibers were found.

Conclusion

A detailed examination of two samples of Johnson and Johnson's Baby Powder, batch numbers 108T and 109T has shown this material to be substantially free of asbestiform minerals. A few tremolite rods were observed in both samples at a level less than 0.5%. No chrysotile has been detected.

Respectfully submitted,

Ian M. Stewart

Manager, Electron Optics Group